

Metamark MDP-H-B

100 micron High Tack Blockout Vinyl



Product Description

MDP-H-B has a high tack adhesive to solve the problem of adhesion onto smooth low energy surfaces, such as Polypropylene, Polyethylene and ABS, as well as for durable graphics on extreme sports equipment. The 100 micron film makes it suitable for print and cut labels and easy application. The grey pigmented solvent-based adhesive to provide increased opacity, so as to obscure the substrate. It also offers an ideal solution for printable wall coverings, enhancing the opportunities available for wall décor.

Handling and Printing Guidelines

- Ensure that the material has reached room temperature and a relative humidity of 50% before printing.
- Do not handle the face film directly and ensure it is free from dust and static.
- Suitable for use on Solvent, Eco Solvent, Latex and U.V. inkjet printers. Always perform a test print first.
- Ensure that the correct profiles and heater settings are used. Most profiles are available for download from www.metamark.co.uk.

Overlaminating

- Overlaminating is recommended to prevent abrasion and to extend colour fastness.
- Allow the inks to cure before overlaminating, this is usually 24-48 hours.
- The matched laminate for MDP-H is MetaGuard 305 or 302. For all other laminates the user should determine suitability.

Application

- Allow the inks to cure before cutting or overlaminating, usually 24-48 hours. Perform cut path as separate operation to avoid edge curl.
- Not recommended for heavily textured surfaces. The user should determine suitability of substrate, refer to the web site.
- Refer to www.metamark.co.uk for application guidelines.

Face Film

Face Film:	Monomeric calendered PVC
Gauge:	100 micron nominal
Tensile Strength	60N/25mm MD / 52N/25mm TD nom.
Elongation at break	180% MD nominal

Adhesive

Type	High-tack perm. Grey Solvent-based acrylic
Weight	23gsm nominal
Adhesion LDPE 20 min	5N/25mm nominal
24 hour	15 N/25mm nominal
Adhesion Steel 20 min	22 N/25mm nominal
24 hour	28 N/25mm nominal
Adhesion Glass 20 min	22 N/25mm nominal
24 hour	28 N/25mm nominal
Perceived tack	High
Application temperature	+5°C to +60°C
Service temperature	-30°C to +100°C

Release Liner

Weight	140 gsm nominal
Type	Layflat kraft paper with PE coating

Finishes

Finishes Available	MDP-H-B-200	White Gloss
	MDP-H-B-301M	White Matt

Roll Presentation

Roll sizes and net weights	760mm x 50m	11kg
	1370mm x 50m	20kg
	1600mm x 50m	23kg
Presentation	Face film outwards, on a 76mm core.	

Durability

Shelf Life	1 year
Fire Rating	Self-extinguishing. The fire rating is a function of the substrate.
External weathering	4 years. This refers to the unprinted vinyl when installed. Refer to ink manufacturer for durability of the finished product.
Chemical Resistance	Unprinted film resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali, eg. Diesel oil, gasoline, paraffin, hydraulic oil, antifreeze.
Regulations	REACH and RoHS compliant

Warranty: Metamark (UK) Limited warrants to its customers that graphics produced using Metamark Digital Media will remain in good condition without excessive fading or colour degradation for the specified life time of the ink used, when correctly stored, printed and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark DigitalVinyl becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converter is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. **Please Note:** The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.

Metamark (UK) Limited

○ Luneside • New Quay Road • Lancaster • LA1 5QP • Tel +44 (0)1524 387140 • Fax +44 (0)1524 387147

○ Metamark House • Octimum Business Park • Forsyth Road • Woking • GU21 5SF • Tel +44 (0)1483 571111 • Fax +44 (0)1483 570540

sales@metamark.co.uk

www.metamark.co.uk